

# TAPAJUNTAS

## JOINT MATERIAL GROUT

Cement-based joint filling mortar **type CG2 AW** European standard **UNE-EN 13888**

### TECHNICAL CHARACTERISTICS



#### QUALITATIVE COMPOSITION

**Hydraulic conglomerate:** White cement with a high strength resistance. **Mineral charges:** Silica with controlled granulometries. **Additives:** Plasticizers, water repellent, special additives and resins.

#### PHYSICAL ANALYSIS


Pot life	120 minutes	Abrasion strength	< 2000 mm <sup>3</sup> EN 12808-2
Appearance	White and colours	Fineness	< 0,15 mm
Bulk density of dust	1,5 ± 0,2 g/cm <sup>3</sup>	Contraction	≤ 1,5 mm
Bending strength after 28 days	≥ 3,5 N / mm <sup>2</sup> EN 12808-3	Mix water	34% aprox. (1,7 L. / saco 5kg)
Compression strength after 28 days	≥ 15 N / mm <sup>2</sup> EN 12808-3		

Results obtained under conditions of 22°C temperature and 50% relative humidity. This results may vary depending on the weather conditions.

#### HOW TO USE

- Add clean water and mix energetically with a mechanical agitator until you get an homogeneous mass with a kind of creamy consistence, let stand 5 to 10 minutes and proceed with its application with a plastic or rubber trowel or any traditional means.
- Allow it to dry for 40 minutes (depending on the temperature conditions) and proceed to clean using a slightly damp sponge.
- **Under no circumstances wait more than 1 h to proceed to clean.**
- Only once it has hardened we can proceed to clean it with a dry and clean cloth.
- Allow a minimum of 24 hours after laying the floor and 48 hours on the wall covering.
- Apply this product on any dust and scale clean joint for better adhesion.
- For rough tiles or high external porosity, protect them with a primer to avoid stains on the tiles.
- The application temperature must be between 5°C and 30°C.

#### USES



#### SECURITY



Gloves



Goggles



Mask

#### INDICATIONS OF USE

Material for filling types I, IIA, IIB and III tiles on walls and floors both indoors and outdoors. Water and abrasion resistant. This product is indicated to proceed to fill joints up to 10mm without cracking them. We have available a premium grout more flexible and anti-mold, special for swimming pools.

#### PACKAGING, PRESERVATION AND STORAGE

The product is available in bags of 5 kg. In boxes of 6 units. The shelf life of the product is 12 months from the date of manufacture in its original packaging. Store in a aired/breezy place, protected from the environment and soil moisture.

#### AVAILABLE COLOURS

White, polar white, ivory, vanilla, cream, beige, pistachio, yellow, salmon, orange, terracotta, clear brown, dark brown, 6c brown, red, violet, blue, clear green, pearl grey, cement grey, dark grey, anthracite and black



The colour scheme of the colors presented here, are indicative, since the colours may vary when applying the product

#### IMPORTANT

The indications for the use, as well as the results of the tests expressed in this document, have been written according to our own knowledge and the result of rigorous controls carried out in our laboratory. The final consumer must be sure, that the product chosen is suitable for the application to be made. The responsibility of our company will be limited to the value of the merchandise used, since the final use of our product by qualified personnel is beyond our control.

MANUFACTURED BY **CEMI-COLA, PORT S.L.**

C/ Isaac Newton, 83 / Pol. Ind. Sepes / 46500 Sagunto - Valencia SPAIN / Tel. and Fax (+34) 96 266 27 62 / cemicola@cemicola.com